

TECHNICAL DATA SHEET

Dry lubricant spray PTFE

Art. no. 0893 550

P. Qty.: 1 / 6

Dry lubrication, does not attract dirt and dust

- Remedies squeaking, creaking and jamming
- Dry lubrication
- Film thickness of 10 µm enables use with extremely small tolerances
- Very high resistance
- Silicone-free
- Mineral oil-free



Chemical basis	Polytetrafluoroethylene
Colour	Milky-transparent (protective film)
Density	0,6 g/cm ³
Smell/fragrance	Characteristic
Min. temperature conditions	-180 °C
Max. temperature conditions	260 °C
Boiling point	-44 °C
VOC concentration (CH)	588,66 g/l
Silicone-free	Yes
Acid-free	Yes
Resin-free	Yes
Mineral oil-free	Yes
AOX-free	Yes
Contents	300 ml
Container	Aerosol can
Shelf life from production	24 Month

Application area

Transparent, dirt-resistant dry lubricant for light to medium loads.

Application information

Suitable for dry lubrication of friction points. With minimal and medium load, can be used for metals, plastic, rubber etc. Ideal for sliding roof and seat rails, door hinges and locks, sliding doors, bottom hung windows, window locks, furniture hinges, drawers, runners, ball bearings, electrical switches etc., also suitable as a release agent with economical application.

Notice

Smokers must wash their hands after use. Smoking contaminated tobacco products may cause health-related issues.

TECHNICAL DATA SHEET

The usage instructions are recommendations based on the tests we have conducted and based on our experience; carry out your own tests before each application. Due to the large number of applications and storage and processing conditions, we do not assume any liability for a specific application result. Insofar as our free customer service provides technical information or acts as an advisory service, no responsibility is assumed by this service except where the advice or information given falls within the scope of our specified, contractually agreed service or the advisor was acting deliberately. We guarantee consistent quality of our products. We reserve the right to make technical changes and carry out further development.